

Ferritic chromium-molybdenum dual-stabilized stainless steel

Type 18Cr-2Mo-Ti stainless steel:
EN 1.4521, AISI 444

Applications

- Boilers, water heaters and heat exchangers are typical applications for grade 1.4521. Also storage tanks and tubes are suitable applications.
- This grade may also be used in pipes for tap water and in other use for drinking-water contexts.
- High chromium content and addition of molybdenum makes this grade an alternative for "acid-proof" austenitic grades for some selected applications.

Welding

- Conventional welding methods and filler materials applied to austenitic 300-series can be used. Heat input in welding should be kept in a minimum level.
- Shielding gases should be based on Ar/He and not to contain hydrogen, nitrogen or carbon dioxide, respectively.
- Generally welded structures show lower ductility compared to that of base material.

Fabrication

- Grade 1.4521 can be formed using typical forming processes like folding, bending, drawing, etc.
- It has higher minimum proof strength than standard austenitic stainless steel grade 1.4301 / AISI 304 in combination with lower work hardening behavior.
- Due to the stabilization, the r-value is higher compared to the non-stabilized ferritic stainless steel such as 1.4016.
- These characteristics means excellent deep-drawability.

Corrosion resistance

- Outokumpu produces grade 1.4521 with a typical chromium content of 18 wt-% and molybdenum content of 2 wt-%.
- Resistance to localized corrosion is close to grade 1.4404 / AISI 316 "acid-proof" austenitic.
- Grade 1.4521 is not susceptible to chloride induced stress corrosion cracking.
- In chloride containing solutions pitting and crevice corrosion is possible depending on various parameters like chloride concentration, temperature, pH value, redox potential, crevice geometry and others.
- The best material performance is reached usually with the help of adequate design, correct post-weld treatment and regular cleaning during use (if applicable).

Physical properties

- Crystal structure is ferritic, and therefore material is ferromagnetic as soft annealed condition.
- Density: 7,7 g/cm³
- Coefficient of thermal expansion: 10,4x10⁻⁶1/K (T = 20...100 °C)
- Thermal conductivity at 20°C: 23 W/(m x K)
- Modulus of elasticity at 20°C: 220 GPa

Mechanical properties

- For cold rolled materials.

	Grade	Proof strength R _{p0,2} (N/mm ²)	Tensile strength R _m (N/mm ²)	Elongation after fracture A (%)
EN	1.4521	Min. 300	420...640	Min. 20
AISI	444	Min. 275	Min. 415	Min. 20

- Minimum values of 0,2 % proof strength (R_{p0,2}, N/mm²) at elevated temperatures, EN 10088-2.

EN	100	150	200	250	300	350
1.4521	250	240	230	220	210	205

Chemical compositions (typical)

EN	C	Cr	Mo	Ni	Ti+Nb	Fe
	wt-%	wt-%	wt-%	wt-%	wt-%	wt-%
1.4521	0,02	18,0	2,0	-	0,5	Bal.

Further information

- Standard Specification EN 10088-2:2005
- Standard Specification ASTM A 240 - 08
- Technical Customer Service

Disclaimer:

Information given in this document may be amended without notice. Care has been taken to ensure that the contents are accurate but Outokumpu and its affiliated companies makes no warranty underrating and have no liability for the anything in this document unless explicitly agreed in writing.

Outokumpu Tornio Works

FI-95400 Tornio, Finland
Tel. +358 16 4521, Fax +358 16 452 620, www.outokumpu.com
Domicile: Tornio, Finland. Business ID 0823315-9, VAT FI08233159